

SPECIFICATION

anyS!gn!
anyFlex!



บริษัท จีเทคโอเอชเอ็ม จำกัด
G-TECH OHM CO.,LTD.
ศูนย์ค้าส่งวัสดุสิ่งพิมพ์นานาชนิด

SUPER BACKLIT / CODE : SBL-I-X.XX-50M

APPLICATION

Light box graphic
Backlit Trade show display
Department store display, Transit Displays
Luminous advertising
Metro illuminated signage
P.O.P. Display
Self-adhesive vinyl, Screen printing and digital printing

COMPATIBILITY

Ink Compatibility

ECO



Solvent



UV-
Curable



Printer Compatibility

Most Solvent & Eco Solvent, UV Curable Printing system : LATEX &
HP, Agfa-Jeti, Epson, Roland, Mimaki, Mutoh, Seiko, Océ, VUTEK, Scorpion, Keundo, etc.

SPECIFICATION

Caliper 0.45 mm.
weight 500 g/m²
Base material Polyester
Surface Gloss
Width 0.92, 1.22, 1.32, 1.52, 1.82, 2.22,
2.52, 2.82, 3.20 m.
Length 50 m.
Yarn x Thread 300x500 (18x12)

TEST RESULTS

TEARING STRENGTH PERFORMANCE REPORT			
Report No	Largest Force(N)	TEARING STRENGTH (KN/M)	AREA(MM2)
1 (woof)	260.49	25.047	10.4
2(woof)	254	24.423	10.4
3(woof)	279.36	26.862	10.4
4(longitude)	310.5	29.856	10.4
5(longitude)	309.6	29.769	10.4
6(longitude)	313.11	30.107	10.4
AVERAGE	287.85	27.677	10.4

TENSILE TESTING PERFORMANCE REPORT			
Report No	Largest Force(N)	TENSILE STRENGTH (MPa)	AREA(MM2)
1 (woof)	326.85	31.428	10.4
2(woof)	318.66	30.640	10.4
3(woof)	332.29	31.951	10.4
4(longitude)	423.67	40.738	10.4
5(longitude)	431.34	41.475	10.4
6(longitude)	410.33	39.455	10.4
AVERAGE	373.86	35.948	10.4

GUIDELINES

Printing Tip : Dry time will vary depending on ink type.

Storage : It is recommended to store in the closed original packing in a cool and dry environment

Shelf Life : One year stored in original package in recommended condition

Information provided here is subject to our test criteria and subject to change without prior notice. No media warranty is implied.

All material should be tested by purchaser to determine final suitability. Printer and ink change may affect results.